

絶縁熱接着フィルム SJ41

Thermo-setting Electrical Isolation Film SJ41

薄膜で優れた接着性能 5 μ m から提供可能

Thin and strong adhesion, available from 5 μ m

薄膜で部品の低背化や熱抵抗低減に貢献

Contributes to height reduction and lower thermal resistance with thin thickness

常温で保管可能

Can be stored at room temperature

段差追従性が良好

Excellent adaptability to height differences

用途例 Application

■ 受動部品（チップ抵抗器など）

Passive components like chip resistor

■ 自動車用部品

Automotive parts (motor cores, etc.)

■ 各種装置部品・治具

Various equipment parts and jigs

■ FPC や FFC 等回路基板材料

Circuit board materials such as FPC and FFC

※以下のような素材に適用可能です。

Applicable to following materials lamination.

金属：ステンレス、銅、アルミ、ニッケルなど

Metal: Stainless, Copper, Aluminum, Nickel, etc

樹脂・無機素材：ポリイミド・ガラスエポキシ・FRP・アルミナ・ガラスなど

Resin・Inorganic materials: Polyimide, Glass epoxy, FRP, Alumina, Glass, etc

データおよび層構成 Data and layer structure

特性項目 Items	20 μ m品 代表値 Data
ピール強度 (被着体：SUS304) Peel strength (Adhered material: SUS304)	17N/cm
絶縁破壊電圧(DC) Dielectric breakdown voltage	230KV/mm
吸湿率 Moisture Absorption Rate	0.24% (JIS K7209 D法に準拠) (JIS K7209 D method)
長期耐熱性 Long-term heat resistance	150°C×1,000H ピール強度の低下なし No reduction in peel strength

保護フィルム Protection film

接着フィルム (5~20 μ m)
Adhesive layer

保護フィルム Protection film

※ご要望に応じてカスタムも可能です。 Customization available upon request.

